
# **PLEXUS** Structural Bonding Solutions for Rail Manufacturers



Contact us to conduct an assembly line audit to find out if Plexus<sup>®</sup> is right for you! cs@itwpp.com




### **Structural Bonding Solutions for Rail Manufacturers**

Product	Description	Mixed color	Mix ratio (by volume)	Working time (mins)	Tensile strength (psi)	Tensile elongation (%)	P	shinin co				A COLORINAL COLORINA	\$ \$\]		and a contraction of the second	de 55	200 200 200 200 200 200 200 200 200 200
MA8110	Next-generation primerless multimaterial adhesive	Gray	1:1	8 - 12	3,350	40 - 70	++	++	++	++	++	++	++	++	++	++	++
MA8120	Next-generation primerless multimaterial adhesive	Gray	1:1	18 - 22	2,750	50 - 80	++	++	++	++	++	++	++	++	++	++	++
MA205HV	Fastest primerless to metal adhesive	Green	10:1	3 - 5	2,250	20 - 50	++	++	++	++	++	-	-	+	++	++	++
MA830	Primerless to metal adhesive	Gray	10:1	4 - 6	3,500	30 - 60	++	++	++	++	++	-	-	+	++	+*	++
MA832	Primerless to metal adhesive - medium open time	Gray	10:1	12 - 16	2,,850	30 - 60	++	++	++	++	++	-	-	+	++	+*	++
MA420	All purpose toughened adhesive	Blue	10:1	4 - 6	2,850	30 - 50	+*	++	+*	++	++	-	-	-	++	++	++
MA320	Excellent low temp impact, white UV stable	White	10:1	8 - 12	1,950	60 - 100	+*	++	+*	++	+*	-	-	-	++	+*	++


++ Excellent adhesion with no to little surface preparation. + Good adhesion with some surface preparation. - Not recommended. \* Use PC120 Cleaner Conditioner for optimum long term environmental durability

#### Improved durability with uniform stress distribution



#### Improved structure strengths with tougher materials

**Energy to Break on Cold Rolled Steel** 



## Plexus is a registered trademark of Illinois Tool Works, Inc. © 2019 Plexus – © 2019 ITW Performance Polymers, July 2019. The technical information, recommendations and other statements contained in this sheet are based upon tests or experience that ITW Performance Polymers believes are reliable, but the accuracy or completeness of such information is not guaranteed. The information provided is not intended to substitute for the customers own testing.